

## **AMENDMENTS TO THE CLAIMS:**

This listing of claims will replace all prior versions and listings of claims in the application.

### **Listing Of Claims:**

Claim 1. (Currently Amended): A thermoplastic molding composition comprising

- A) aromatic polycarbonate and/or polyester carbonate,
- B) impact modifier
- C) optionally, thermoplastic homopolymer and/or copolymer,
- D) a combination of

D.1 phosphorus compound and

D.2 ~~phosphorus/oxygen compound different from D.1 or phosphorus/sulfur compound or the reaction product of D.1 and D.2.~~ that is different from D.1 is at least one member selected from the group consisting of phosphorus oxide, phosphorus sulfide, aluminum phosphate, alkaline-earth phosphate, alkali phosphate and ammonium phosphate.


Claim 2. (Original): The composition of Claim 1 wherein D is present in an amount of 0.1 to 30 parts by weight.

Claim 3. (Original): The composition of Claim 1 wherein D.2 is a phosphorus/oxygen compound.

Claim 4. (Original): The composition of Claim 1, wherein D.1 is at least one monomeric or oligomeric member selected from the group consisting of

phosphoric acid ester, phosphonic acid ester, phosphonate amine and phosphazene.

Claim 5. (Original): The composition of Claim 1 wherein D.1 conforms to the general formula (III)



where


$\text{R}^1$ ,  $\text{R}^2$ ,  $\text{R}^3$  and  $\text{R}^4$  independently of one another denote an optionally halogenated  $\text{C}_1$ - to  $\text{C}_8$ -alkyl, or an optionally substituted by alkyl, and/or halogen  $\text{C}_5$ - to  $\text{C}_6$ -cycloalkyl,  $\text{C}_6$ - to  $\text{C}_{20}$ -aryl or  $\text{C}_7$ - to  $\text{C}_{12}$ -arylalkyl,

$n$  is, independently of one another, 0 or 1,

$q$  is 0 to 30 and

$X$  is a mononuclear or polynuclear aromatic radical containing 6 to 30 carbon atoms, or a linear or branched aliphatic radical containing 2 to 30 carbon atoms, optionally OH-substituted and contain up to 8 ether bonds.

Claim 6. (Original): The composition of Claim 5, wherein X in formula (III) stands for



or their chlorinated or brominated derivatives.


Claim 7. (Original): The composition of Claim 5 wherein component D.1 is at least one member selected from the group consisting of monophosphate, and oligophosphate .

Claim 8. (Original): The composition of Claim 1 wherein D.1 is at least one member selected from among phosphonate amine conforming to formula (IV)




in which

A stands for a radical of formula (Va)



or (Vb)



$R^{11}$  and  $R^{12}$  stand, independently of one another, for unsubstituted or substituted  $C_1$ - $C_{10}$ -alkyl or for unsubstituted or substituted  $C_6$ - $C_{10}$ -aryl,



$R^{13}$  and  $R^{14}$  stand, independently of one another, for unsubstituted or substituted  $C_1$ - $C_{10}$ -alkyl or unsubstituted or substituted  $C_6$ - $C_{10}$ -aryl or

$R^{13}$  and  $R^{14}$  together denote an unsubstituted or substituted heterocyclic ring of 3 to 10 carbon atoms, and

y is 0, 1 or 2 and

$B^1$  stands independently for hydrogen, optionally halogenated  $C_2$ - $C_8$ -alkyl, unsubstituted or substituted  $C_6$ - $C_{10}$ -aryl

a phosphazene conforming to formulae (VIa) and (VIb)



wherein

R is in each case identical or different and stands for amino, in each case optionally halogenated,  $C_1$ - to  $C_8$ -alkyl or  $C_1$ - to  $C_8$ -alkoxy, in each case optionally substituted by alkyl,  $C_4$ -alkyl, and/or halogen-substituted  $C_5$ - to  $C_6$ -cycloalkyl,  $C_6$ - to  $C_{20}$ -aryl,  $C_6$ - to  $C_{20}$ -aryloxy, or  $C_7$ - $C_{12}$ -aralkyl,

k is an integer of 0 to 15.

Claim 9. (Cancelled).

Claim 10. (Currently Amended): The composition of Claim ~~[[9]]~~ 1 wherein phosphorus oxide is phosphorous pentoxide.

Claim 11. (Original): The composition of Claim 1 further containing an anti-dripping agent.

Claim 12. (Original): The composition of Claim 1 wherein impact modifier is a graft polymer of

B.1 5 to 95 wt % of at least one vinyl monomer on

B.2 95 to 5 wt % of one or more graft bases having glass-transition temperatures lower than 10°C.

Claim 13. (Original): The composition of Claim 12 wherein B.1 contains

B.1.1. 50 to 99 parts by weight of at least one member selected from the group consisting of vinyl aromatic, nucleus-substituted vinyl aromatics and C<sub>1</sub>-C<sub>4</sub>-alkyl methacrylates, and

B.1.2 1 to 50 parts by weight of at least one member selected from the group consisting of vinyl cyanide, C<sub>1</sub>-C<sub>8</sub>-alkyl methacrylate and a derivative of unsaturated carboxylic acid.

Claim 14. (Original): The composition of Claim 13 wherein B1.1 is at least one member selected from the group consisting of styrene,  $\alpha$ -methylstyrene and methyl methacrylate and wherein B.1.2 is at least one member selected from the group consisting of acrylonitrile, maleic anhydride and methyl methacrylate.

Claim 15. (Original): The composition of Claim 14 wherein B.1.1 is styrene and B.1.2 is acrylonitrile.

Claim 16. (Original): The composition of Claim 12 wherein the graft base B.2 is at least one member selected from the group consisting of diene rubber, EP(D)M rubber, acrylate rubber, polyurethane rubber, silicon rubber, chloroprene rubber and ethylene/vinyl acetate rubber.

Claim 17. (Original): The composition of Claim 16, wherein diene rubber is a copolymer of diene.

Claim 18. (Original): The composition of Claims 1 wherein said C is at least one member selected from the group consisting of thermoplastic vinyl (co)polymer and polyalkylene terephthalate.

Claim 19. (Original): The composition of Claim 11 wherein the anti-dripping agent is fluorinated polyolefin.

Claim 20. (Original): A thermoplastic molding composition comprising

A) 40 to 99 parts by weight of aromatic polycarbonate and/or polyester carbonate,

B) 0.5 to 60 parts by weight of a graft polymer of

B.1) 5 to 95 wt. % relative to the weight of B of one or more vinyl monomers on

B.2) 95 to 5 wt. % relative to the weight of B of one or more graft bases having a glass-transition temperature lower than 10°C,

C) 0 to 45 parts by weight of at least one thermoplastic polymer selected from the group consisting of vinyl (co)polymer and polyalkylene terephthalate,

D) 0.1 to 30 parts by weight of a combination of

D.1) organic phosphorus compound and

D.2) a phosphorus/oxygen compound or phosphorus/sulfur compound and

E) 0 to 5 parts by weight of an anti-dripping agent,

wherein the sum of the parts by weight of the components A-E is 100.

Claim 21. (Original): A method of using the composition of Claim 1 comprising producing molded articles.

Claim 22. (Original): A molded article comprising the composition of Claim 1.